

SEALOSTICK

HDPE SURFACED BITUMINOUS WATERPROOFING MEMBRANE

DESCRIPTION

SEALOSTICK is a self-adhesive polymer modified bituminous, waterproofing sheet membrane, laminated onto a tough HDPE film on one side and a silicone release film on the other. **SEALOSTICK** conforms to the requirements of BS 8102.

USES

- ⇒ Cold applied, self-adhesive and easy to apply.
- ⇒ Excellent adhesion to vertical and horizontal surfaces.
- ⇒ Excellent resistance to chlorides, sulphates, dilute alkalis and acids.
- ⇒ Good tear and puncture resistance.
- ⇒ Water and vapor-proof.

APPLICATION INSTRUCTIONS

The application temperature should be between 10 °C to 55 °C. Application procedures may vary slightly depending upon site conditions. The general recommended guidelines for the application of the self-adhesive waterproofing system is as follows:

Surface Preparation

The surface shall be cleaned thoroughly of all contaminants like dust, traces of curing compound, oil and grease. All surface imperfections, protrusions, structurally unsound and friable concrete must be removed and repaired with a suitable concrete repair mortar.

Priming

Apply **CHEMCOAT SB** or any other equivalent bituminous primer or solvent-based primer @ 4-6 m²/L to a clean, smooth and dry surface by brush, roller or spray. Allow the primer to dry prior to the application of the membrane. As the viscosity of the primer is low, it easily penetrates into concrete pores which promotes the adhesion between the membrane and the concrete surface. In addition, the primer also acts as a binder for the dust which gets accumulated on the surface even after cleaning.

Alignment

Start the installation of all membrane plies from the low point or drains, so that the flow of water is over or parallel to the plies, but never against the laps. All overlaps at the membrane seams shall be installed so as to have 'up' slope laps over 'down' slope laps. Begin membrane application by unrolling the roll of **SEALOSTICK** membrane and aligning the side laps.

Protection

The membrane shall be protected from damage due to ongoing site activities or from aggregates during backfilling by **PROTECTOBOARD**. Alternatively, on horizontal areas, the membrane can also be protected by laying a screed.

CHARACTERISTICS

SEALOSTICK is used as waterproofing or damp-proofing membrane intended for concrete protection. It may be used for horizontal and vertical application for tanking below ground structures, subways and retaining walls.

COLOURS

Available in standard flooring colours and in clear. Other colours can be matched upon request.

STORAGE AND SHELF-LIFE

SEALOSTICK membranes must be stored in a shaded area on wooden pallets neatly covered with a thick fabric and tied securely in a manner that will minimize exposure to sunlight and UV. The membrane shall be protected from all sources of heat. The shelf-life is 12 months if stored as per recommendations. Excessive exposure to sunlight, UV and other sources of heat will result in considerable deterioration of the product and reduce its shelf-life.

TYPE



WATER
PROOFING

ADVANTAGES



CHEMICAL
RESISTANT



PUNCTURE
RESISTANT

COMPONENT

1

PART

SEALOSTICK

HDPE SURFACED BITUMINOUS WATERPROOFING MEMBRANE

TECHNICAL SPECIFICATION

Properties		Values		Test Standards
✓	Thickness, mm	1.5	2.0	DIN EN 1849-1
✓	Mass per unit area, kg/m2	1.6	2.1	DIN EN 1849-1
✓	Top Surfacing	HDPE film		-
✓	Softening Point (R&B), °C	> 105		ASTM D 36
✓	Tensile Strength (Film), N/mm2	Long 20		ASTM D 882
		Trans 20		
✓	Elongation At Break (Film), %	Long 300		ASTM D 882
		Trans 300		
✓	Adhesion Strength, N/mm			ASTM D 1004
	Prime Substrate			
	Self			
✓	Puncture Resistance, N	> 220		ASTM E 154
✓	Hydrostatic Pressure@5 bar, (50m)	No leakage		BS EN 12390 (Part 8)
✓	Water Absorption (Film) @24 hours, %	0.14		ASTM D 570
✓	Low Temperature Flexibility, °C	< -15		ASTM D 1970
✓	Crack Bridging Ability, mm	> 1		ASTM C 836
✓	Application Temperature, °C	10 to 55		-
✓	Service Temperature, °C	4 to 80		-

HEALTH & SAFETY

SEALOSTICK contains a tacky bitumen compound which can stick to human skin during application. Bitumen stains can be removed by using a cloth dipped in a suitable cleaner.

PACKAGING

1m x 20m x 1.5mm per roll, 1m x 15m x 2.0mm per roll.

Legal Notes:

'Statements made in this bulletin are for the assistance of our customers. They are based on our experience and judgment but must not be regarded as amounting to a legal warranty or as involving any liability on our part. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of this product must test the product's suitability for the intended application and purpose. CHEMIND reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. Users may always refer to the most recent issue of our Product Data Sheet for the products concerned, copies of which will be supplied upon request.'

Made In Malaysia

SCOPE OF REGISTRATION AND STANDARDS

Manufacture of Waterproofing materials. Compliance with ASTM technical standards and AS 3740 - 2004 Australia Standard. SIRIM certification is available for selected products upon request, subject to applicable testing and certification requirements.



MANUFACTURER:
CHEMIND INDUSTRIES SDN. BHD. (468913-T)
NO. 8, JALAN MERANTI JAYA 16, TAMAN PERINDUSTRIAN MERANTI JAYA,
47100 PUCHONG, SELANGOR DARUL EHSAN, MALAYSIA.
TEL: 603-8066 4128 FAX: 603- 8051 3128

